

广州海关技术中心

GUANGZHOU CUSTOMS DISTRICT TECHNOLOGY CENTER



中国认可
国家承认
检测
CNAS L2322

国家食品接触材料检测重点实验室(广东)

NATIONAL REFERENCE LABORATORY FOR FOOD CONTACT MATERIAL (GUANGDONG)

地址: 广东省广州市先烈中路100号15栋之一中国商检大厦6-7楼

Address: 6-7/F., China's Commodity Inspection Building, No.100, Xianlie Middle Road, Yuexiu District, Guangzhou, Guangdong, China

电话 | Tel.: +86-020-3829 0551 邮编 | P.C.: 510070 网址 | WS.: www.iqtcnet.cn

检测报告 Test Report

报验号/No.: R0723000394

日期/Date: 2023/08/30

页码/Page: 1/22

申请人 Applicant: 大连歌瑞恩实业有限公司
Greenwood (Dalian) Industrial Co., Ltd
地址 Address: 大连市金州区华家街道杨家店村
YANGJIADIAN VILLAGE, HUAJIA STREET, JINZHOU DISTRICT, DALIAN City,
LIAONING PROVINCE, CHINA
申报品名 Commodity declared: 110 木勺 110 wooden spoon
样品数量 Sample quantity: 1 批 1 batch
样品标记 Sample identifier: 110 木勺, 同材质产品: 110 咖啡棒; 140 木制咖啡棒; 176 木制咖啡棒; 140 木刀; 140 木叉; 140 木勺; 165 木刀; 160 木叉; 160 木勺; 85 果叉; 95 平铲; 100 木勺; 170 木刀; 170 木叉; 84 木勺; 125 木叉; 100 木叉; 140 叉勺
110 wooden spoon, The same material products: 110 wooden stirrers; 140 wooden stirrers; 176 wooden stirrers; 140 wooden knife; 140 wooden fork; 140 wooden spoon; 165 wooden knife; 160 wooden fork; 160 wooden spoon; 85 wooden snack fork; 95 wooden spoon; 100 wooden spoon; 170 wooden knife; 170 wooden fork; 84 wooden spoon; 125 wooden fork; 100 wooden fork; 140 spork
申报材质 Material declared: FSC 100% 桦木 乌克兰 FSC 100% Birch UKRAINE
一次性/重复性 Single/Repeat use: 一次性 Single use
是否婴幼儿专用 Only for infants: 否 No
接触食品类型 Food type(s): 全类型 All types of food
接触条件 Food contact conditions: 40°C < T ≤ 70°C, 15min < t ≤ 1h
收样时间 Date of sample received: 2023/08/02
测试时间 Test period: 2023/08/02 ~ 2023/08/15
测试方法 Test methods: 请参见下一页 Please refer to the next page
测试结果 Test results: 请参见下一页 Please refer to the next page
结论 Conclusion:

上述样品所检项目由申请人指定, 检测结果符合 FDA 21 CFR 178.3800, GB 4806.12-2022 和 GB 9685-2016 的相关要求。

As specified by the applicant, the test results of the samples indicated above are in compliance with the relevant requirements of FDA 21 CFR 178.3800, GB 4806.12-2022 and GB 9685-2016.

(续下页/ followed by the next page)



access code: 638807

报告批准人
/Authorized
signatory:

钟怀宁

检验检测专用章
(07)
4401060154269

钟怀宁 Zhong Huaining、陈文锐 Chen Wenrui

Verification platform: <https://css.iqtcnet.cn>

国家食品接触材料检测重点实验室(广东)

NATIONAL REFERENCE LABORATORY FOR FOOD CONTACT MATERIAL (GUANGDONG)

地址: 广东省广州市先烈中路100号15栋之一中国商检大厦6-7楼

Address: 6-7/F., China's Commodity Inspection Building, No.100, Xianlie Middle Road, Yuexiu District, Guangzhou, Guangdong, China

电话 | Tel.: +86-020-3829 0551 邮编 | P.C.: 510070 网址 | WS.: www.iqtenet.cn

检测报告 Test Report

报验号/No.: R0723000394

日期/Date: 2023/08/30

页码/Page: 2/22

(1) 样品信息/Sample information:

申报品名 Commodity declared	IQTC 样品描述 IQTC sample description	S/V (dm ² /kg)
110 木勺 110wooden spoon	原色木勺 Primary color wooden spoon	6

(2) 测试结果/Test result:

申报品名 Commodity declared	判定依据 Regulation	测试项目 Test item	测试方法 Test method	限量 Limit	测试结果 Result	单位 Unit	评价 Comment
110 木勺 110wooden spoon	FDA 21 CFR 178.3800	五氯苯酚 Pentachlorophenol	SN/T 2145-2008	≤50	<0.1**	ppm	合格 Pass
	EN 71-3:2019#	铬 Chromium	EN 71-3:2019	≤460	<5**	mg/kg	合格 Pass
		硒 Selenium	EN 71-3:2019	≤460	<5**	mg/kg	合格 Pass
		汞 Mercury	EN 71-3:2019	≤94	<5**	mg/kg	合格 Pass
		锑 Antimony	EN 71-3:2019	≤560	<5**	mg/kg	合格 Pass
		钡 Barium	EN 71-3:2019	≤18750	17.7	mg/kg	合格 Pass
		镉 Cadmium	EN 71-3:2019	≤17	<5**	mg/kg	合格 Pass
		铅 Lead	EN 71-3:2019	≤23	<3**	mg/kg	合格 Pass
		砷 Arsenic	EN 71-3:2019	≤47	<5**	mg/kg	合格 Pass
	GB 4806.12-2022	感官(样品) Sensory(sample)	GB 4806.12-2022	色泽正常,无毛刺、异臭、霉斑或其他污物 Normal color, no burr, no foreign odor, no mildew or other impurities	合格 Pass	--	合格 Pass
感官(浸泡液) Sensory(simulant)		GB 4806.12-2022	迁移试验所得浸泡液不应有沉淀、异臭、异常着色等感官性能的劣变 Simulants from migration test should be no sediment, foreign odor, abnormal colorization or other sensory deterioration	合格 Pass	--	合格 Pass	

1. 本报告结果仅对测试样品负责。The results in this report are relevant only to the sample(s) tested.

2. 未经签发机构书面同意,不得部分引述或复制本报告。Without written permission of IQTC, this report shall not be quoted or reproduced except in full.

国家食品接触材料检测重点实验室 (广东)

NATIONAL REFERENCE LABORATORY FOR FOOD CONTACT MATERIAL (GUANGDONG)

地址: 广东省广州市先烈中路100号15栋之一中国商检大厦6-7楼

Address: 6-7/F., China's Commodity Inspection Building, No.100, Xianlie Middle Road, Yuexiu District, Guangzhou, Guangdong, China

电话 | Tel.: +86-020-3829 0551 邮编 | P.C.: 510070 网址 | WS.: www.iqtenet.cn

检测报告 Test Report

报验号/No.: R0723000394

日期/Date: 2023/08/30

页码/Page: 3/22

申报品名 Commodity declared	判定依据 Regulation	测试项目 Test item	测试方法 Test method	限量 Limit	测试结果 Result	单位 Unit	评价 Comment
110 木勺 110 wooden spoon	GB 4806.12-2022	甲醛迁移量 (4%乙酸,70°C,2h) Migration of formaldehyde (4% acetic acid,70°C,2h)	GB 31604.48-2016 (第一法 1 st method)	≤15	<0.36**	mg/kg	合格 Pass
		二氧化硫迁移量 (蒸馏水,70°C,2h) Migration of sulfur dioxide (distilled water,70°C,2h)	GB 4806.12-2022 附录 A Annex A	≤10	<1.0**	mg/kg	合格 Pass
		五氯苯酚及其盐类 (以五氯苯酚计) (95%乙醇,60°C,2h) Migration of pentachlorophenol and its salts (expressed as pentachlorophenol) (95% ethanol,60°C,2h)	GB 31604.1-2015, GB 5009.156-2016, SN/T 2204-2015	≤0.15	<0.1**	µg/kg	合格 Pass
		邻苯基苯酚 2-Phenylphenol	GB 4806.12-2022 附录 B Annex B	≤4.8	<0.30**	mg/kg	合格 Pass
		噻菌灵 Thiabendazole	GB 4806.12-2022 附录 B Annex B	≤1.2	<0.30**	mg/kg	合格 Pass
		抑霉唑 Imazalil	GB 4806.12-2022 附录 B Annex B	≤0.4	<0.30**	mg/kg	合格 Pass
		联苯 Biphenyl	GB 4806.12-2022 附录 B Annex B	≤0.6	<0.30**	mg/kg	合格 Pass
		大肠菌群 ^α Coliform ^α	GB 14934-2016 附录 B B.1 Annex B B.1	不得检出 ND	未检出 ND	/50cm ²	合格 Pass
	沙门氏菌 ^α Salmonella ^α	GB 14934-2016 附录 C Annex C	不得检出 ND	未检出 ND	/50cm ²	合格 Pass	
GB 9685-2016	双酚 A 迁移量 (4%乙酸,70°C,2h) Migration of 4,4'-isopropylidene-biphenol (BPA) (4% acetic acid,70°C,2h)	GB 31604.10-2016	≤0.6	<0.01**	mg/kg	合格 Pass	

1. 本报告结果仅对测试样品负责。The results in this report are relevant only to the sample(s) tested.

2. 未经签发机构书面同意,不得部分引述或复制本报告。Without written permission of IQTC, this report shall not be quoted or reproduced except in full.

国家食品接触材料检测重点实验室(广东)

NATIONAL REFERENCE LABORATORY FOR FOOD CONTACT MATERIAL (GUANGDONG)

地址: 广东省广州市先烈中路100号15栋之一中国商检大厦6-7楼

Address: 6-7/F., China's Commodity Inspection Building, No.100, Xianlie Middle Road, Yuexiu District, Guangzhou, Guangdong, China

电话 | Tel.: +86-020-3829 0551 邮编 | P.C.: 510070 网址 | WS.: www.iqtenet.cn

检测报告 Test Report

报验号/No.: R0723000394

日期/Date: 2023/08/30

页码/Page: 4/22

申报品名 Commodity declared	判定依据 Regulation	测试项目 Test item	测试方法 Test method	限量 Limit	测试结果 Result	单位 Unit	评价 Comment
110 木勺 110 wooden spoon	GB 9685-2016	丙烯酰胺迁移量 (4%乙酸,70°C,2h) Migration of acrylamide (4% acetic acid,70°C,2h)	GB 31604.18-2016	ND (DL=0.01)	<0.01*	mg/kg	合格 Pass
		叔二丁基羟基甲苯(BHT)迁移量 (95%乙醇,60°C,2h) Migration of 2,6-Di-tert-butyl-4- methylphenol(BHT) (95% ethanol,60°C,2h)	FCM-3-702-161 (HPLC)	≤3	<0.5**	mg/kg	合格 Pass
		邻苯二甲酸二异壬酯(DINP)迁移量 (异辛烷,40°C,0.5h) Migration of diisononyl phthalate(DINP) (isooctane,40°C,0.5h)	GB 31604.30-2016	≤9	<0.1**	mg/kg	合格 Pass
		邻苯二甲酸二烯丙酯(DAP)迁移量 (异辛烷,40°C,0.5h) Migration of diallyl phthalate(DAP) (isooctane,40°C,0.5h)	GB 31604.30-2016	ND (DL=0.01)	<0.01**	mg/kg	合格 Pass
		邻苯二甲酸二正丁酯(DBP)迁移量 (异辛烷,40°C,0.5h) Migration of dibutyl phthalate(DBP) (isooctane,40°C,0.5h)	GB 31604.30-2016	≤0.3	<0.1**	mg/kg	合格 Pass
	邻苯二甲酸二(α-乙基己酯)(DEHP) 迁移量 (异辛烷,40°C,0.5h) Migration of bis(2-ethylhexyl) phthalate(DEHP) (isooctane,40°C,0.5h)	GB 31604.30-2016	≤1.5	<0.1**	mg/kg	合格 Pass	
	/	邻苯二甲酸二异丁酯(DIBP)迁移量 (异辛烷,40°C,0.5h) Migration of diisobutyl phthalate(DIBP) (isooctane,40°C,0.5h)	GB 31604.30-2016	/	<0.1**	mg/kg	/

1. 本报告结果仅对测试样品负责。The results in this report are relevant only to the sample(s) tested.

2. 未经签发机构书面同意,不得部分引述或复制本报告。Without written permission of IQTC, this report shall not be quoted or reproduced except in full.

国家食品接触材料检测重点实验室(广东)

NATIONAL REFERENCE LABORATORY FOR FOOD CONTACT MATERIAL (GUANGDONG)

地址: 广东省广州市先烈中路100号15栋之一中国商检大厦6-7楼

Address: 6-7/F., China's Commodity Inspection Building, No.100, Xianlie Middle Road, Yuexiu District, Guangzhou, Guangdong, China

电话 | Tel.: +86-020-3829 0551 邮编 | P.C.: 510070 网址 | WS.: www.iqtenet.cn

检测报告 Test Report

报验号/No.: R0723000394

日期/Date: 2023/08/30

页码/Page: 5/22

申报品名 Commodity declared	判定依据 Regulation	测试项目 Test item	测试方法 Test method	限量 Limit	测试结果 Result	单位 Unit	评价 Comment
110 木勺 110 wooden spoon	/	邻苯二甲酸二乙酯(DEP)迁移量 (异辛烷,40°C,0.5h) Migration of diethyl phthalate(DEP) (isooctane,40°C,0.5h)	GB 31604.30-2016	/	<0.1**	mg/kg	/
		邻苯二甲酸二戊酯(DPP)迁移量 (异辛烷,40°C,0.5h) Migration of dipentyl phthalate(DPP) (isooctane,40°C,0.5h)	GB 31604.30-2016	/	<0.1**	mg/kg	/
		邻苯二甲酸二壬酯(DNP)迁移量 (异辛烷,40°C,0.5h) Migration of dinonyl phthalate(DNP) (isooctane,40°C,0.5h)	GB 31604.30-2016	/	<0.1**	mg/kg	/
		邻苯二甲酸二甲酯(DMP)迁移量 (异辛烷,40°C,0.5h) Migration of dimethyl phthalate(DMP) (isooctane,40°C,0.5h)	GB 31604.30-2016	/	<0.1**	mg/kg	/
		邻苯二甲酸二己酯(DHXP)迁移量 (异辛烷,40°C,0.5h) Migration of dihexyl phthalate(DHXP) (isooctane,40°C,0.5h)	GB 31604.30-2016	/	<0.1**	mg/kg	/
		邻苯二甲酸二环己酯(DCHP)迁移量 (异辛烷,40°C,0.5h) Migration of dicyclohexyl phthalate(DCHP) (isooctane,40°C,0.5h)	GB 31604.30-2016	/	<0.1**	mg/kg	/
		邻苯二甲酸二苯酯(DPhP)迁移量 (异辛烷,40°C,0.5h) Migration of diphenyl phthalate(DPhP) (isooctane,40°C,0.5h)	GB 31604.30-2016	/	<0.1**	mg/kg	/
		邻苯二甲酸二(4-甲基-2-戊基)酯(BMPP)迁移量 (异辛烷,40°C,0.5h) Migration of bis(4-methyl-2-pentyl) phthalate(BMPP) (isooctane,40°C,0.5h)	GB 31604.30-2016	/	<0.1**	mg/kg	/

1. 本报告结果仅对测试样品负责。The results in this report are relevant only to the sample(s) tested.

2. 未经签发机构书面同意,不得部分引述或复制本报告。Without written permission of IQTC, this report shall not be quoted or reproduced except in full.

国家食品接触材料检测重点实验室(广东)

NATIONAL REFERENCE LABORATORY FOR FOOD CONTACT MATERIAL (GUANGDONG)

地址: 广东省广州市先烈中路100号15栋之一中国商检大厦6-7楼

Address: 6-7/F., China's Commodity Inspection Building, No.100, Xianlie Middle Road, Yuexiu District, Guangzhou, Guangdong, China

电话 | Tel.: +86-020-3829 0551 邮编 | P.C.: 510070 网址 | WS.: www.iqtenet.cn

检测报告 Test Report

报验号/No.: R0723000394

日期/Date: 2023/08/30

页码/Page: 6/22

申报品名 Commodity declared	判定依据 Regulation	测试项目 Test item	测试方法 Test method	限量 Limit	测试结果 Result	单位 Unit	评价 Comment
110 木勺 110 wooden spoon /		邻苯二甲酸二(2-乙氧基)乙酯(DEEP)迁移量 (异辛烷,40°C,0.5h) Migration of bis(2-ethoxyethyl) phthalate(DEEP) (isooctane,40°C,0.5h)	GB 31604.30-2016	/	<0.1**	mg/kg	/
		邻苯二甲酸二(2-甲氧基)乙酯(DMEP)迁移量 (异辛烷,40°C,0.5h) Migration of bis(2-methoxyethyl) phthalate(DMEP) (isooctane,40°C,0.5h)	GB 31604.30-2016	/	<0.1**	mg/kg	/
		邻苯二甲酸二(2-丁氧基)乙酯(DBEP)迁移量 (异辛烷,40°C,0.5h) Migration of bis(2-n-butoxyethyl) phthalate(DBEP) (isooctane,40°C,0.5h)	GB 31604.30-2016	/	<0.1**	mg/kg	/
		邻苯二甲酸二正辛酯(DNOP)迁移量 (异辛烷,40°C,0.5h) Migration of di-n-octyl phthalate(DNOP) (isooctane,40°C,0.5h)	GB 31604.30-2016	/	<0.1**	mg/kg	/
		邻苯二甲酸丁基苯基酯(BBP)迁移量 (异辛烷,40°C,0.5h) Migration of benzyl butyl phthalate(BBP) (isooctane,40°C,0.5h)	GB 31604.30-2016	/	<0.1**	mg/kg	/
		全氟辛基磺酸锂含量(CAS 29457-72-5) Lithium perfluorooctanesulfonate Content (CAS 29457-72-5)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		全氟辛基磺酸铵含量(CAS 29081-56-9) Ammonium perfluorooctanesulfonate Content (CAS 29081-56-9)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		全氟辛基磺酸钾含量(CAS 2795-39-3) Potassium heptadecafluoro-1-octanesulfonate Content (CAS 2795-39-3)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		全氟辛酸铵含量(CAS 3825-26-1) Ammonium perfluorocaprilate Content (CAS 3825-26-1)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/

1. 本报告结果仅对测试样品负责。The results in this report are relevant only to the sample(s) tested.

2. 未经签发机构书面同意, 不得部分引述或复制本报告。Without written permission of IQTC, this report shall not be quoted or reproduced except in full.

国家食品接触材料检测重点实验室(广东)

NATIONAL REFERENCE LABORATORY FOR FOOD CONTACT MATERIAL (GUANGDONG)

地址: 广东省广州市先烈中路100号15栋之一中国商检大厦6-7楼

Address: 6-7/F., China's Commodity Inspection Building, No.100, Xianlie Middle Road, Yuexiu District, Guangzhou, Guangdong, China

电话 | Tel.: +86-020-3829 0551 邮编 | P.C.: 510070 网址 | WS.: www.iqtenet.cn

检测报告 Test Report

报验号/No.: R0723000394

日期/Date: 2023/08/30

页码/Page: 7/22

申报品名 Commodity declared	判定依据 Regulation	测试项目 Test item	测试方法 Test method	限量 Limit	测试结果 Result	单位 Unit	评价 Comment
110 木勺 110 wooden spoon	/	全氟辛酸钠含量(CAS 335-95-5) Sodium perfluorooctanoate Content (CAS 3335-95-5)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		全氟辛酸银含量(CAS 335-93-3) Silver(I) perfluorooctanoate Content (CAS 335-93-3)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		全氟辛酸钾含量(CAS 2395-00-8) Potassium perfluorooctanoate Content (CAS 2395-00-8)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		全氟癸烷磺酸钾含量(CAS 2806-16-8) Potassium Henicosafuorodecanesulphonate Content (CAS 2806-16-8)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		全氟辛基磺酰氟含量(CAS 307-35-7) Perfluorooctylsulfonylfluoride Content (CAS 307-35-7)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		全氟癸基磺酸铵含量(CAS 67906-42-7) Ammonium Henicosafuorodecanesulphonate Content (CAS 67906-42-7)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		全氟己基磺酸钠含量(CAS 82382-12-15) Sodium Perfluorohexanesulfonate Content (CAS 82382-12-15)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		全氟己基磺酸钾含量(CAS 3871-99-6) Potassium Perfluorohexanesulfonate Content (CAS 3871-99-6)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		全氟癸酸钠含量(CAS 3830-45-3) Sodium nonadecafluorodecanoate Content (CAS 3830-45-3)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		全氟癸酸铵含量(CAS 3108-42-7) Ammonium nonadecafluorodecanoate Content(CAS 3108-42-7)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		全氟壬酸钠含量(CAS 21049-39-8) Sodium perfluorocaprilate Content (CAS 21049-39-8)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/

1. 本报告结果仅对测试样品负责。The results in this report are relevant only to the sample(s) tested.

2. 未经签发机构书面同意, 不得部分引述或复制本报告。Without written permission of IQTC, this report shall not be quoted or reproduced except in full.

国家食品接触材料检测重点实验室 (广东)

NATIONAL REFERENCE LABORATORY FOR FOOD CONTACT MATERIAL (GUANGDONG)

地址: 广东省广州市先烈中路100号15栋之一中国商检大厦6-7楼

Address: 6-7/F., China's Commodity Inspection Building, No.100, Xianlie Middle Road, Yuexiu District, Guangzhou, Guangdong, China

电话 | Tel.: +86-020-3829 0551 邮编 | P.C.: 510070 网址 | WS.: www.iqtenet.cn

检测报告 Test Report

报验号/No.: R0723000394

日期/Date: 2023/08/30

页码/Page: 8/22

申报品名 Commodity declared	判定依据 Regulation	测试项目 Test item	测试方法 Test method	限量 Limit	测试结果 Result	单位 Unit	评价 Comment
110 木勺 110 wooden spoon	/	全氟十八酸含量(CAS 16517-11-6) Perfluorooctadecanoic acid Content (CAS 16517-11-6)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		全氟十六酸含量(CAS 67905-19-5) Perfluorohexadecanoic acid Content (CAS 67905-19-5)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		全氟丁酸含量(CAS 375-22-4) Perfluorobutanoic acid Content (CAS 375-22-4)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		全氟癸烷磺酸盐含量(CAS 2806-15-7) Sodium Perfluorodecane Sulfonate Content(CAS 2806-15-7)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		2H,2H-全氟癸酸含量(CAS 27854-31-5) 2H,2H-Perfluorodecane Acid Content (CAS 27854-31-5)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		1H,1H,2H,2H-全氟-1-十二醇含量 (CAS 865-86-1) 1H,1H,2H,2H-Perfluoro-1-dodecanol Content(CAS 865-86-1)	FCM-3-702-142 (GC-MS)	/	<0.5*	mg/kg	/
		1H,1H,2H,2H-全氟-1-癸醇含量 (CAS 678-39-7) 1H,1H,2H,2H-Perfluoro-1-decanol Content(CAS 678-39-7)	FCM-3-702-142 (GC-MS)	/	<0.5*	mg/kg	/
		1H,1H,2H,2H-全氟-1-辛醇含量 (CAS 647-42-7) 1H,1H,2H,2H-Perfluoro-1-octanol Content(CAS 647-42-7)	FCM-3-702-142 (GC-MS)	/	<0.5*	mg/kg	/
		1H,1H,2H,2H-全氟-1-己醇含量 (CAS 2043-47-2) 1H,1H,2H,2H-Perfluoro-1-hexanol Content(CAS 2043-47-2)	FCM-3-702-142 (GC-MS)	/	<0.5*	mg/kg	/
		1H,1H,2H,2H-全氟十二醇丙烯酸酯含量 (CAS 17741-60-5) 1H,1H,2H,2H-Perfluorododecylacrylate Content(CAS 17741-60-5)	FCM-3-702-142 (GC-MS)	/	<0.5*	mg/kg	/

1. 本报告结果仅对测试样品负责。The results in this report are relevant only to the sample(s) tested.

2. 未经签发机构书面同意, 不得部分引述或复制本报告。Without written permission of IQTC, this report shall not be quoted or reproduced except in full.

国家食品接触材料检测重点实验室 (广东)

NATIONAL REFERENCE LABORATORY FOR FOOD CONTACT MATERIAL (GUANGDONG)

地址: 广东省广州市先烈中路100号15栋之一中国商检大厦6-7楼

Address: 6-7/F., China's Commodity Inspection Building, No.100, Xianlie Middle Road, Yuexiu District, Guangzhou, Guangdong, China

电话 | Tel.: +86-020-3829 0551 邮编 | P.C.: 510070 网址 | WS.: www.iqtenet.cn

检测报告 Test Report

报验号/No.: R0723000394

日期/Date: 2023/08/30

页码/Page: 9/22

申报品名 Commodity declared	判定依据 Regulation	测试项目 Test item	测试方法 Test method	限量 Limit	测试结果 Result	单位 Unit	评价 Comment
110 木勺 110 wooden spoon	/	1H,1H,2H,2H-全氟癸醇丙烯酸酯含量 (CAS 27905-45-9) 1H,1H,2H,2H-Perfluorodecylacrylate Content(CAS 27905-45-9)	FCM-3-702-142 (GC-MS)	/	<0.5*	mg/kg	/
		1H,1H,2H,2H-全氟辛醇丙烯酸酯含量 (CAS 17527-29-6) 1H,1H,2H,2H-Perfluorooctylacrylate Content(CAS 17527-29-6)	FCM-3-702-142 (GC-MS)	/	<0.5*	mg/kg	/
		11H-全氟癸烷羧酸含量(CAS 1765-48-6) 11H-Perfluoro decan carboxylate Content(CAS 1765-48-6)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		7H-十二氟庚烷羧酸含量(CAS 1546-95-8) 7H-Dodecafluoro heptane carboxylate Content(CAS 1546-95-8)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		3,7-二甲基全氟辛烷羧酸含量 (CAS 172155-07-6) Perfluoro-3-7-dimethyl octane carboxylate Content(CAS 172155-07-6)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		2H,2H,3H,3H-全氟十一酸含量 (CAS 34598-33-9) 2H,2H,3H,3H-Perfluoroundecanoic acid Content(CAS 34598-33-9)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		1H,1H,2H,2H-全氟辛烷磺酸含量 (CAS 27619-97-2) 1H,1H,2H,2H-Perfluorooctanesulphonic acid Content(CAS 27619-97-2)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		N-乙基全氟辛磺酰胺乙醇含量 (CAS 1691-99-2) N-Ethyl-Perfluorooctanesulfonamidoethanol Content(CAS 1691-99-2)	FCM-3-702-142 (GC-MS)	/	<0.5*	mg/kg	/
		N-乙基全氟磺酰胺含量(CAS 4151-50-2) N-Ethyl-Perfluorooctanesulfonamide Content(CAS 4151-50-2)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/

1. 本报告结果仅对测试样品负责。The results in this report are relevant only to the sample(s) tested.

2. 未经签发机构书面同意, 不得部分引述或复制本报告。Without written permission of IQTC, this report shall not be quoted or reproduced except in full.

国家食品接触材料检测重点实验室(广东)

NATIONAL REFERENCE LABORATORY FOR FOOD CONTACT MATERIAL (GUANGDONG)

地址: 广东省广州市先烈中路100号15栋之一中国商检大厦6-7楼

Address: 6-7/F., China's Commodity Inspection Building, No.100, Xianlie Middle Road, Yuexiu District, Guangzhou, Guangdong, China

电话 | Tel.: +86-020-3829 0551 邮编 | P.C.: 510070 网址 | WS.: www.iqtenet.cn

检测报告 Test Report

报验号/No.: R0723000394

日期/Date: 2023/08/30

页码/Page: 10/22

申报品名 Commodity declared	判定依据 Regulation	测试项目 Test item	测试方法 Test method	限量 Limit	测试结果 Result	单位 Unit	评价 Comment
110 木勺 110 wooden spoon	/	N-甲基全氟磺酰胺含量(CAS 31506-32-8) N-Methyl-Perfluorooctanesulfonamide Content(CAS 31506-32-8)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		全氟辛烷磺酰胺含量(CAS 754-91-6) Perfluorooctanesulfonamide Content (CAS 754-91-6)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		全氟癸烷磺酸含量(CAS 335-77-3) Perfluorodecanesulfonic acid Content (CAS 335-77-3)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		全氟辛烷磺酸含量(CAS 1763-23-1) Perfluorooctanesulfonic acid Content (CAS 1763-23-1)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		全氟己烷磺酸含量(CAS 355-46-4) Perfluorohexanesulfonic acid Content (CAS 355-46-4)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		全氟丁烷磺酸含量(CAS 375-73-5) Perfluorobutanesulfonic acid Content (CAS 375-73-5)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		全氟十四酸含量(CAS 376-06-7) Perfluorotetradecanoic acid Content (CAS 376-06-7)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		全氟十三酸含量(CAS 72629-94-8) Perfluorotridecanoic acid Content (CAS 72629-94-8)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		全氟十二酸含量(CAS 307-55-1) Perfluorododecanoic acid Content (CAS 307-55-1)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		全氟十一酸含量(CAS 2058-94-8) Perfluoroundecanoic acid Content (CAS 2058-94-8)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		全氟癸酸含量(CAS 335-76-2) Perfluorodecanoic acid Content (CAS 335-76-2)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/

1. 本报告结果仅对测试样品负责。The results in this report are relevant only to the sample(s) tested.

2. 未经签发机构书面同意, 不得部分引述或复制本报告。Without written permission of IQTC, this report shall not be quoted or reproduced except in full.

国家食品接触材料检测重点实验室(广东)

NATIONAL REFERENCE LABORATORY FOR FOOD CONTACT MATERIAL (GUANGDONG)

地址: 广东省广州市先烈中路100号15栋之一中国商检大厦6-7楼

Add.: 6-7/F., China's Commodity Inspection Building, No.100, Xianlie Middle Road, Yuexiu District, Guangzhou, Guangdong, China

电话 | Tel.: +86-020-3829 0551 邮编 | P.C.: 510070 网址 | WS.: www.iqtenet.cn

检测报告
Test Report

报验号/No.: R0723000394

日期/Date: 2023/08/30

页码/Page: 11/22

申报品名 Commodity declared	判定依据 Regulation	测试项目 Test item	测试方法 Test method	限量 Limit	测试结果 Result	单位 Unit	评价 Comment
110 木勺 110 wooden spoon	/	全氟壬酸含量(CAS 375-95-1) Perfluorononanoic acid Content (CAS 375-95-1)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		全氟辛酸含量(CAS 335-67-1) Perfluorooctanoic acid Content (CAS 335-67-1)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		全氟庚酸含量(CAS 375-85-9) Perfluoroheptanoic acid Content (CAS 375-85-9)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		全氟己酸含量(CAS 307-24-4) Perfluorohexanoic acid Content (CAS 307-24-4)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/
		全氟戊酸含量(CAS 2706-90-3) Perfluoropentanoic acid Content (CAS 2706-90-3)	FCM-3-702-142 (LC-MS/MS)	/	<0.5*	mg/kg	/

*检出限 Limit of detection

**定量限 Limit of quantitation

#送检样品不在标准适用范围内,根据申请人要求测试,限值供参考。

#The test was performed as specified by the applicant. The submitted sample is out of the scope of the standard. Limit is for reference only.

α该项目测试地点: 中国广州市天河区珠江新城花城大道 66 号 B 座, 授权签字人: 陈文锐

Test site: Tower B, No.66 Huacheng Avenue, Zhujiang Xincheng, Tianhe District, Guangzhou, China, Authorized signatory: Chen Wenrui

广州海关技术中心

GUANGZHOU CUSTOMS DISTRICT TECHNOLOGY CENTER



中国认可
国家承认
检测
CNAS L2322

国家食品接触材料检测重点实验室(广东)

NATIONAL REFERENCE LABORATORY FOR FOOD CONTACT MATERIAL (GUANGDONG)

地址: 广东省广州市先烈中路100号15栋之一中国商检大厦6-7楼

Address: 6-7/F., China's Commodity Inspection Building, No.100, Xianlie Middle Road, Yuexiu District, Guangzhou, Guangdong, China

电话 | Tel.: +86-020-3829 0551 邮编 | P.C.: 510070 网址 | WS.: www.iqtenet.cn


检测报告 Test Report

报验号/No.: R0723000394

日期/Date: 2023/08/30

页码/Page: 12/22

样品照片/Sample photo:



其他样品信息/ Other sample information provided by applicant:

样品名称 Sample Name	型号/规格 Type specification	材质 Material	备注 Remarks
140 wooden spoon	140	桦木 Birch	乌克兰 UKRAINE
140 wooden knife	140	桦木 Birch	乌克兰 UKRAINE
140 wooden fork	140	桦木 Birch	乌克兰 UKRAINE
160 wooden spoon	160	桦木 Birch	乌克兰 UKRAINE
165 wooden knife	165	桦木 Birch	乌克兰 UKRAINE
160 wooden fork	160	桦木 Birch	乌克兰 UKRAINE
100 wooden spoon	100	桦木 Birch	乌克兰 UKRAINE
170 wooden knife	170	桦木 Birch	乌克兰 UKRAINE
170 wooden fork	170	桦木 Birch	乌克兰 UKRAINE
84 wooden spoon	84	桦木 Birch	乌克兰 UKRAINE
95 wooden spoon	95	桦木 Birch	乌克兰 UKRAINE
100 wooden fork	100	桦木 Birch	乌克兰 UKRAINE
85 wooden snack fork	85	桦木 Birch	乌克兰 UKRAINE
125 wooden fork	125	桦木 Birch	乌克兰 UKRAINE
176 wooden stirrers	176	桦木 Birch	乌克兰 UKRAINE
110 wooden stirrers	110	桦木 Birch	乌克兰 UKRAINE
140 wooden stirrers	140	桦木 Birch	乌克兰 UKRAINE
140 spork	140	桦木 Birch	乌克兰 UKRAINE
172 wooden fork	172	桦木 Birch	乌克兰 UKRAINE
170 wooden spoon	170	桦木 Birch	乌克兰 UKRAINE

1. 本报告结果仅对测试样品负责。The results in this report are relevant only to the sample(s) tested.

2. 未经签发机构书面同意, 不得部分引述或复制本报告。Without written permission of IQTC, this report shall not be quoted or reproduced except in full.

地址: 广东省广州市先烈中路100号15栋之一中国商检大厦6-7楼

Add.: 6-7/F., China's Commodity Inspection Building, No.100, Xianlie Middle Road, Yuexiu District, Guangzhou, Guangdong, China

电话 | Tel.: +86-020-3829 0551 邮编 | P.C.: 510070 网址 | WS.: www.iqtenet.cn

检测报告 Test Report

报验号/No.: R0723000394


日期/Date: 2023/08/30

页码/Page: 13/22

其它样品照片/ Photos of other sample:



140 wooden spoon



140 wooden knife

地址: 广东省广州市先烈中路100号15栋之一中国商检大厦6-7楼

Address: 6-7/F., China's Commodity Inspection Building, No.100, Xianlie Middle Road, Yuexiu District, Guangzhou, Guangdong, China

电话 | Tel.: +86-020-3829 0551 邮编 | P.C.: 510070 网址 | WS.: www.iqtenet.cn

检测报告 Test Report

报验号/No.: R0723000394

日期/Date: 2023/08/30

页码/Page: 14/22



140 wooden fork



160 wooden spoon

广州海关技术中心

GUANGZHOU CUSTOMS DISTRICT TECHNOLOGY CENTER



中国认可
国家承认
检测
CNAS L2322

国家食品接触材料检测重点实验室(广东)

NATIONAL REFERENCE LABORATORY FOR FOOD CONTACT MATERIAL (GUANGDONG)

地址: 广东省广州市先烈中路100号15栋之一中国商检大厦6-7楼

Add.: 6-7/F., China's Commodity Inspection Building, No.100, Xianlie Middle Road, Yuexiu District, Guangzhou, Guangdong, China


电话 | Tel.: +86-020-3829 0551 邮编 | P.C.: 510070 网址 | WS.: www.iqtenet.cn

检测报告 Test Report

报验号/No.: R0723000394

日期/Date: 2023/08/30

页码/Page: 15/22



165 wooden knife



160 wooden fork

1. 本报告结果仅对测试样品负责。The results in this report are relevant only to the sample(s) tested.
2. 未经签发机构书面同意, 不得部分引述或复制本报告。Without written permission of IQTC, this report shall not be quoted or reproduced except in full.

地址: 广东省广州市先烈中路100号15栋之一中国商检大厦6-7楼

Address: 6-7/F., China's Commodity Inspection Building, No.100, Xianlie Middle Road, Yuexiu District, Guangzhou, Guangdong, China

电话 | Tel.: +86-020-3829 0551 邮编 | P.C.: 510070 网址 | WS.: www.iqtenet.cn

检测报告 Test Report

报验号/No.: R0723000394

日期/Date: 2023/08/30

页码/Page: 16/22



100 wooden spoon



170 wooden knife

地址: 广东省广州市先烈中路100号15栋之一中国商检大厦6-7楼

Address: 6-7/F., China's Commodity Inspection Building, No.100, Xianlie Middle Road, Yuexiu District, Guangzhou, Guangdong, China


电话 | Tel.: +86-020-3829 0551 邮编 | P.C.: 510070 网址 | WS.: www.iqtenet.cn

检测报告 Test Report


报验号/No.: R0723000394

日期/Date: 2023/08/30

页码/Page: 17/22



170 wooden fork



84 wooden spoon

地址: 广东省广州市先烈中路100号15栋之一中国商检大厦6-7楼

Address: 6-7/F., China's Commodity Inspection Building, No.100, Xianlie Middle Road, Yuexiu District, Guangzhou, Guangdong, China


电话 | Tel.: +86-020-3829 0551 邮编 | P.C.: 510070 网址 | WS.: www.iqtenet.cn

检测报告 Test Report


报验号/No.: R0723000394

日期/Date: 2023/08/30

页码/Page: 18/22



95 wooden spoon



100 wooden fork

地址: 广东省广州市先烈中路100号15栋之一中国商检大厦6-7楼

Address: 6-7/F., China's Commodity Inspection Building, No.100, Xianlie Middle Road, Yuexiu District, Guangzhou, Guangdong, China


电话 | Tel.: +86-020-3829 0551 邮编 | P.C.: 510070 网址 | WS.: www.iqtenet.cn

检测报告 Test Report


报验号/No.: R0723000394

日期/Date: 2023/08/30

页码/Page: 19/22



85 wooden snack fork



125 wooden fork

广州海关技术中心

GUANGZHOU CUSTOMS DISTRICT TECHNOLOGY CENTER



中国认可
国家承认
检测
TESTING
CNAS L2322

国家食品接触材料检测重点实验室(广东)

NATIONAL REFERENCE LABORATORY FOR FOOD CONTACT MATERIAL (GUANGDONG)

地址: 广东省广州市先烈中路100号15栋之一中国商检大厦6-7楼

Address: 6-7/F., China's Commodity Inspection Building, No.100, Xianlie Middle Road, Yuexiu District, Guangzhou, Guangdong, China


电话 | Tel.: +86-020-3829 0551 邮编 | P.C.: 510070 网址 | WS.: www.iqtenet.cn

检测报告 Test Report


报验号/No.: R0723000394

日期/Date: 2023/08/30

页码/Page: 20/22



176 wooden stirrers



110 wooden stirrers

1. 本报告结果仅对测试样品负责。The results in this report are relevant only to the sample(s) tested.
2. 未经签发机构书面同意, 不得部分引述或复制本报告。Without written permission of IQTC, this report shall not be quoted or reproduced except in full.

地址: 广东省广州市先烈中路100号15栋之一中国商检大厦6-7楼

Add.: 6-7/F., China's Commodity Inspection Building, No.100, Xianlie Middle Road, Yuexiu District, Guangzhou, Guangdong, China


电话 | Tel.: +86-020-3829 0551 邮编 | P.C.: 510070 网址 | WS.: www.iqtenet.cn

检测报告 Test Report


报验号/No.: R0723000394

日期/Date: 2023/08/30

页码/Page: 21/22



140 wooden stirrers



140 spork

地址: 广东省广州市先烈中路100号15栋之一中国商检大厦6-7楼

Add.: 6-7/F., China's Commodity Inspection Building, No.100, Xianlie Middle Road, Yuexiu District, Guangzhou, Guangdong, China

电话 | Tel.: +86-020-3829 0551 邮编 | P.C.: 510070 网址 | WS.: www.iqtenet.cn

检测报告 Test Report


报验号/No.: R0723000394

日期/Date: 2023/08/30

页码/Page: 22/22



172 wooden fork



170 wooden spoon

本报告所述申请人、地址、申报品名、样品标记、申报材质、使用条件和其它样品信息等信息均为申请人提供, 实验室不负责其真实性。

The information mentioned in the report including applicant, address, commodity declared, sample identifier, material declared, conditions of use and other sample information etc. is provided by applicant. Laboratory is not responsible for authenticity.

备注: 2023年8月16日所发报验号 0723000394 证书作废。

Remarks: The certificate No 0723000394 released on 16 August 2023 is abolished.

报告结束/End of the report